Small Ball Mill Spare Parts Grinding Balls For Ball Mill 48HRC-60HRC

Basic Information

- Place of Origin:
- Brand Name:
- Certification:

China HYZONT

CCC

ZQCR2

iron basket

15 Days after Payment

L/C, D/A, D/P, T/T

- Model Number:
- Minimum Order Quantity: 1 ton
- Price: Negotiable
- Packaging Details:
- Delivery Time:
- Payment Terms:



Product Specification

Highlight:

48HRC grinding balls for ball mill, 60HRC grinding balls for ball mill, Ball Mill Spare Parts 48HRC

Our Product Introduction

High quality Griding Ball of Ball mill machine 48-60HRC high quality

Chromium Alloy Casting Ball (Forging)



高、中、低铬合金铸球 High, medium and low chromium alloy of metal ball

高、中、低铬合金铸球 typhmedium/two chromum alloy of metal bad	¢ 8	φ10	¢12.5	φ15	φ20	¢25
	¢30	φ40	φ50	¢ 60	φ70	¢ 80
	φ 90	¢ 100	¢110	¢120	¢ 125	¢130

机械性能、金相组织 Mechanical Properties and Microstructure

名 称 Name	硬度 Hardness(HRC)	冲击值 AK(j/cm ²)	金相组织 Microstructure	落球次数 Falling times	
低铬合金铸球 itee chromium disysed casel printing halls	≥45	≥2.0	P+C	8000	
中铬合金铸球 adus chromum dicysel cast gending balts ≥48		≥2.0	P+C	15000	
高铬合金铸球 Might checknium thoyed cast granding balls	≥58	≥2.5	M+C	18000	
特高铬合金铸球 strendly high shrenium disysed cast grinding balls	≥60	≥3.0	M+C	20000	

C-碳化物 M-马氏体 P-珠光体 C-Carbide P-Pear lite M-Martensite

化学成份 Chemical Compostion

化 学 成 份 Chemical Composition							
名 称 Name	С	Si	Mn	Cr	Р	S	Cu Mo Al Ni Nb Zr v
低铬合金铸球 Investment disynchical grinding balls	2.2-3.5	≤1.2	≤0.3-1.5	0.8-2.2	≤0.10	≤0.10	微量 Trace
中铬合金铸球 medua chronium doyed cast grinding balls	2.0-3.3	≤1.2	≤0.3-1.5	4.9-9.0	≤0.10	≪0.10	微量 Trace
高铬合金铸球 High stremum dioyed cast grinding balls	2.0-3.2	≤1.0	≤0.3-1.5	10-12	≤0.10	≤0.06	微量 Trace
特高铬合金铸球 strendty high chircmum dieyed sast grinding balls	2.0-3.2	≪1.0	≤0.3-1.5	18-28	≪0.10	≤0.06	微量 Trace

注:以上产品如需调整化学成份或增加其它合金元素,另以合同方式的定为准 Notes: it shall be negotilated in the contractif the chemical composition is to be adjusted.

Hyzont (Shanghai) Industrial Technologies Co.,Ltd..

+86-15021164313

raymond@hyzont.com

© powerplantmachine.com

Room No.809-811 block No.1, Lane No.99, Shenmei Road, Pudong New District, Shanghai, China.